




ROBUST GROUT 580

High Strength Shrinkage Compensated Grout

SYSTEM DIAGRAM



1. High Strength Concrete
2. **Robust Grout 580**
3. Base Plate

DESCRIPTION

Shrinkage compensated high strength cementitious grout which is suitable for flowable and pumping application

USES

- Heavy duty concrete anchor
- Precast and pre-stressed panel repair and gap filling
- Pumping grout
- Underpinning
- Machine foundation
- Rail beds
- Bridge bearing

BENEFITS

- Fast strength development
- Final strength > 80 N/mm²
- Shrinkage compensated
- Excellent flow
- Chloride free

COMPLIED STANDARD

- ASTM C348, C349, C827, C940, C953

TECHNICAL PROPERTIES

Technical Properties	Trowelable	Flowable
Water Demand	3.2 - 3.6 L	4.2 - 4.6 L
Yield	12.5 L	14 L
Compressive Strength		
1 day	~ 50 N/mm ²	~ 40 N/mm ²
7 days	~ 70 N/mm ²	~ 60 N/mm ²
28 days	~ 90 N/mm ²	~ 80 N/mm ²
Flow Table	140 mm	300 mm
Initial Setting Time	4 hrs	5 hrs
Final Setting Time	5 hrs	6 hrs
Expansion in 24 hrs	~ 0.3%	~ 0.1%
Bleeding	-	No Bleeding

RECOMMENDATION

- For >100 mm thickness, not exceed 1 part of 10 mm granite chip can be added to pourable or flowable **Robust Grout 580**
- **Wall Buddy 155** is recommended to prime the substrate when patching on wall



ROBUST GROUT 580

High Strength Shrinkage Compensated Grout

PHYSICAL FEATURES

Physical Properties	Feature
Package	25 kg
Component	Cement, Green Binder, Expansive Agent, Graded Sand
Aggregate Size	1 mm
Pot Life	30 mins
Chloride Content	No Chloride
Layer Thickness	100 mm

STORAGE

Shelf life is 6 months if stored in dry and cool place

APPLICATION

SUBSTRATE PREPARATION

- Substrate should be free from mould oil, grease, loose particles and contamination of foreign materials
- Rusting of steel bar should be removed
- Formwork should be water tight for formwork repair

MATERIAL PREPARATION

- Select the consistency required
- Mix 1 bag of 25 kg **Robust Grout 580** with suitable amount of water for at least 3 minutes by electrical mixer until homogeneous
- After mixing, add 10 mm granite chip if needed
- Dry-packed consistency can be applied by gloved hand or trowel
- Grouting under baseplate should use pourable consistency
- Pumping application or formwork grouting should use flowable consistency
- Apply the grout with suitable method

CURING

- Natural air curing is sufficient
- For large area application in hot climate, recommended to use wet hessian at the first day curing

SAFETY

Wear NIOSH approved facemask during mixing as to avoid inhaling of dust.

May cause irritation to eyes and skin:

1. In case of contact with eyes, rinse immediately with water and seek for medical advice if needed.
2. In case of contact with skin, rinse immediately with soap and water. To seek medical advice if needed.

HEAD OFFICE:

A-1-3A, Pusat Perdagangan Kuchai, No.2, Jalan 1/127,
Off Jalan Kuchai Lama, 58200 Kuala Lumpur, Malaysia.

T: 603-7982 8066 F: 603-7983 8066 W: www.starkendrymix.com.my

FACTORY:

Lot 12448-12473, Kawasan Perindustrian Bidor,
Mukim Bidor, Daerah Batang Padang,
35500 Bidor, Perak, Malaysia.