


STÄRKEN

**Drymix
Solutions**

TM



Skim Coat Series

FINISH GREY 830

**POLYMER MODIFIED
FINISHING COAT**

**Polymer modified cementitious skim coat.
Can be used as a finishing coat to receive
paint for wall and ceiling**

Uses

- Exterior and interior skim coat wall/ceiling finishing coat
- Suitable for concrete, plaster and render surface
- Hardened surface can be sanded, painted and wall papered

Benefits

- Water resistant
- Ultra-smooth finishing
- Polymer modified and shrinkage compensated to prevent hair line cracks

Complied Standard

| EN 998 | EN 1015 | BS 4551 |

www.starkendrymix.com.my

Skim Coat Series

FINISH GREY 830

POLYMER MODIFIED FINISHING COAT



TECHNICAL PROPERTIES

Adhesive Strength	> 0.5 N/mm ²
Water Retentivity	> 99%
Alkaline Resistance	Good

PHYSICAL FEATURES

Package	Approx. 25kg
Water Demand	10 - 11 ℓ (40 - 44%)
Consumption	1.1 kg/m ² /mm
Binder	Cement, Green Binders
Filler Size	< 0.3 mm
Application Thickness	1 - 2 mm per coat
Pot Life	2 hours

STORAGE

Shelf life is 6 months if stored in dry and cool place

Starken Drymix Solutions Sdn. Bhd.
201001032580 (916505-X)

A-1-3A, Pusat Perdagangan Kuchai,
No.2, Jalan 1/127, Off Jalan Kuchai Lama,
58200 Kuala Lumpur, Malaysia.

T: +603-7982 8066 F: +603-7983 8066

Ver 1.0

STÄRKEN Drymix Solutions

TM

RECOMMENDATION

- 1 To be applied on **Base Grey 820** or **Panel Plaster 638**
- 2 Mix with **Mortar Buddy 152** for application on painted surface
- 3 **Moisture Sealer 186** is recommended for application on gypsum board surface, prior to skim coating works

APPLICATION

SUBSTRATE PREPARATION

- 1 Substrate should be free from mould oil, grease, loose particles and contamination of foreign materials
- 2 Dampening of concrete or plastered substrate is recommended prior to the application of **Finish Grey 830**

MATERIAL PREPARATION

- 1 Mix 1 bag of 25kg **Finish Grey 830** with 10 - 11 ℓ water for at least 3 minutes by electrical mixer until homogeneous
- 2 1 - 2 mm thickness can be applied in 1 coat. After the previous coat is hardened, 2 coats can be build-up and total thickness up to 4mm
- 3 Sand paper polishing is advised to apply within 48 hours
- 4 Paint can be applied at least 3 days after application to reduce the alkalinity

CURING

- 1 Natural air curing is sufficient
- 2 Recommended to apply water mist curing in first 2 days during hot climate

SAFETY

Wear NIOSH approved facemask during mixing as to avoid inhaling of dust. May cause irritation to eyes and skin:

- 1 In case of contact with eyes, rinse immediately with water and seek for medical advice if needed
- 2 In case of contact with skin, rinse immediately with soap and water. To seek medical advice if needed